

Chemical Resistance of Garlock Compressed Sheet and GYLON[®] Gasketing



Garlock
SEALING TECHNOLOGIES[®]

Chemical Resistance of Garlock Compressed Sheet and GYLON®

A general guide for selection of gasketing material

Key: A = Suitable
 B = Depends on operating conditions
 C = Unsuitable
 – = No data or insufficient evidence

Footnotes explained on page 13.

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
Abietic Acid	A	A	A	A	A	A	A	A	–	A	A	–	–	–
Acetaldehyde	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Acetamide	A	A	A	A	A	A	A	A	C	A	A	C	A	B
Acetic Acid (Crude, Glacial, Pure)	A	A	A	A	A	A	A	B	B	B	B	B	B	B
Acetic Anhydride	A	A	A	A	A	A	A	A	A	A	A	A	B	A
Acetone	A	A	A	A	A	A	A	C	B	C	C	B	B	A
Acetonitrile	A	A	A	A	A	A	A	C	–	C	C	–	B	B
Acetophenone	A	A	A	A	A	A	A	C	C	C	C	C	C	B
2-Acetylaminofluorene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Acetylene	A	A	A	A	A	A	A	A	B	A	A ¹²	B	A	B
Acrolein	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	B	C	B	B	C	B	B
Acrylamide	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
Acrylic Acid	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	B
Acrylic Anhydride	A	A	A	A	A	A	A	–	–	–	–	–	–	–
Acrylonitrile	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
Air	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Allyl Acetate	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Allyl Chloride	A	A	A	B	B	A	A	C	C	C	C	C	C	B
Allyl Methacrylate	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Aluminum Chloride	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Aluminum Fluoride	C	–	A	C	C	A	A	A	A	A	A	A	A	A
Aluminum Hydroxide (Solid)	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Aluminum Nitrate	A	A	A	A	A	A	–	B	B	B	B	B	B	B
Aluminum Sulfate	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Alums	A	A	A	B	B	A	A	A	A	A	A	A	A	A
4-Aminodiphenyl	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Ammonia, Gas, 150°F and below	A	A	A	A	A	A	A	A	A	B	A	A	A	A
Gas, Above 150°F	A	A	A	A	A	A	A	C	C	C	C	C	B	B
Liquid, Anhydrous	A	A	A	A	A	A	A	B	–	B	B	–	A	A
Ammonium Chloride	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Ammonium Hydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Nitrate	A	A	A	A	A	A	–	B	B	B	B	B	B	B
Ammonium Phosphate, Monobasic	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Dibasic	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Tribasic	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ammonium Sulfate	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Amyl Acetate	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Amyl Alcohol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Aniline, Aniline Oil	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Aniline Dyes	A	A	A	A	A	A	A	C	B	C	C	B	B	B

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues. GARLOCK is a registered trademark for packings, gaskets, and other products of Garlock.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
o-Anisidine	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Aqua Regia	A	A	A	B	B	A	C	C	C	C	C	C	C	C
Aroclors	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Asphalt	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Aviation Gasoline	A	A	A	A	A	A	A	B	C	B	B	C	B	C
Barium Chloride	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Barium Hydroxide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Barium Sulfide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Baygon	A	A	A	A	A	A	A	C	C	C	C	C	-	-
Beer ¹⁰	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Benzaldehyde	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Benzene, Benzol	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Benzidine	A	A	A	A	A	A	A	C	C	C	C	C	C	-
Benzoic Acid	A	A	A	A	A	A	A	B	B	B	B	B	B	B
Benzonitrile	A	A	A	A	A	A	A	C	-	C	C	-	-	C
Benzotrichloride	A	A	A	C	C	A	A	C	C	C	C	C	C	C
Benzoyl Chloride	A	A	A	-	-	A	A	C	-	C	C	-	C	C
Benzyl Alcohol	A	A	A	A	A	A	A	C	-	C	C	-	B	B
Benzyl Chloride	A	A	A	-	-	A	A	C	C	C	C	C	C	B
Biphenyl	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Bis(2-chloroethyl)ether	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Bis(chloromethyl)ether	A	A	A	-	-	A	A	C	C	C	C	C	C	B
Bis(2-ethylhexyl)phthalate	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Black Sulfate Liquor	C	B	A	C	A	A	A	C	C	C	C	C	C	C
Blast Furnace Gas	A	A	A	A	A	A	A	B	C	B	B	C	B	C
Bleach (Sodium Hypochlorite)	A	A	A	B	B	A	-	C	-	C	C	-	C	C
Boiler Feed Water	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Borax	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Boric Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Brine (Sodium Chloride)	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Bromine	A	A	A	C	C	A	-	C	C	C	C	C	C	C
Bromine Trifluoride	C	C	C	C	C	C	C	C	C	C	C	C	C	C
Bromoform	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Bromomethane	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Butadiene	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	-	C
Butane	A	A	A	A	A	A	A	A	C	B	A ¹²	C	B	C
2-Butanone	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Butyl Acetate	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Butyl Alcohol, Butanol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
n-Butyl Amine	A	A	A	A	A	A	A	B	-	B	B	-	C	B
tert-Butyl Amine	A	A	A	A	A	A	A	B	-	B	B	-	C	B
Butyl Methacrylate	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
Butyric Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium Bisulfite	A	A	A	A	A	A	A	B	-	B	B	-	B	C
Calcium Chloride	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Calcium Cyanamide	A	A	A	A	A	A	A	B	B	B	B	B	B	B

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
Calcium Hydroxide	-	A	A	-	A	A	A	A	A	A	A	A	A	A
Calcium Hypochlorite	A	A	A	B	B	A	-	B	B	B	C	C	C	C ²
Calcium Nitrate	A	A	A	-	-	A	C	B	B	B	B	B	B	B
Calflo AF	A	A	A	A	A	A	A	A	C	A	A	C	-	C
Calflo FG	A	A	A	A	A	A	A	A	C	A	A	C	-	C
Calflo HTF	A	A	A	A	A	A	A	A	C	A	A	C	-	C
Calflo LT	A	A	A	A	A	A	A	A	C	A	A	C	-	C
Cane Sugar Liquors	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Caprolactam	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Captan	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Carbaryl	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Carbolic Acid, Phenol	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Carbon Dioxide, Dry	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Wet	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Carbon Disulfide	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Carbon Monoxide	A	A	A	A	A	A	A	B	B	B	B	B	B	B
Carbon Tetrachloride	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Carbonic Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Carbonyl Sulfide	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Castor Oil	A	A	A	A	A	A	A	A	C	A	A	C	B	B
Catechol	A	A	A	A	A	A	A	C	B	C	C	B	-	-
Caustic Soda	C	B	A ⁶	C	A ⁶	A ¹¹	A ⁶	C	C	C	C	C	C	C
Cetane (Hexadecane)	A	A	A	A	A	A	A	A	C	A	A	C	B	C
China Wood Oil	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Chloramben	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Chlorazotic Acid (Aqua Regia)	A	A	A	B	B	A	C	C	C	C	C	C	C	C
Chlordane	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Chlorinated Solvents, Dry	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Wet	A	A	A	C	C	A	A	C	C	C	C	C	C	C
Chlorine, Dry	A	A	A	A	A	A	A	B	B	B	B	B	B	B
Wet	A	A	A	C	C	A	A	C	C	C	C	C	C	C
Chlorine Dioxide	A	A	A	-	-	A	C	C	C	C	C	C	C	C
Chlorine Trifluoride	C	C	C	C	C	C	C	C	C	C	C	C	C	C
Chloroacetic Acid	A	A	A	C	C	A	A	C	B	C	C	B	C	B
2-Chloroacetophenone	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Chloroazotic Acid (Aqua Regia)	A	A	A	B	B	A	C	C	C	C	C	C	C	C
Chlorobenzene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Chlorobenzilate	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Chloroethane	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Chloroethylene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Chloroform	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Chloromethyl Methyl Ether	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Chloronitrous Acid (Aqua Regia)	A	A	A	B	B	A	C	C	C	C	C	C	C	C
Chloroprene	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Chlorosulfonic Acid	A	A	A	-	-	A	-	C	C	C	C	C	C	C
Chrome Plating Solutions	- ⁵	- ⁵	A	- ⁵	B	A	A	C	C	C	C	C	C	C

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
Chromic Acid	A	A	A	B	B	A	C	C	C	C	C	C	C	C
Chromic Anhydride	A	A	A	B	B	A	C	C	C	C	C	C	C	C
Chromium Trioxide	A	A	A	B	B	A	C	C	C	C	C	C	C	C
Citric Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Coke Oven Gas	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Copper Chloride	A	A	A	C	C	A	A	A	A	A	A	A	A	A
Copper Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Corn Oil ¹⁰	A	A	A	A	A	A	A	A	C	A	A	C	B	B
Cotton Seed Oil ¹⁰	A	A	A	A	A	A	A	A	C	A	A	C	B	B
Creosote	A	A	A	A	A	A	A	B	C	B	B	C	B	C
Cresols, Cresylic Acid	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Crotonic Acid	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Crude Oil	A	A	A	B	B	A	A	A	B	A	A ¹²	B	B	C
Cumene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Cyclohexane	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Cyclohexanone	A	A	A	A	A	A	A	C	C	C	C	C	C	B
2,4-D, Salts and Esters	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Detergent Solutions	B	B	A	B	A	A	A	A	A	A	A	A	A	A
Diazomethane	A	A	A	A	A	A	A	-	-	-	-	-	-	-
Dibenzofuran	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dibenzylether	A	A	A	A	A	A	A	C	C	C	C	C	C	C
1,2-Dibromo-3-chloropropane	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Dibromoethane	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dibutyl Phthalate	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Dibutyl Sebacate	A	A	A	A	A	A	A	C	C	C	C	C	C	B
o-Dichlorobenzene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
1,4-Dichlorobenzene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
3,3-Dichlorobenzidine	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Dichloroethane (1,1 or 1,2)	A	A	A	A	A	A	A	C	C	C	C	C	C	C
1,1-Dichloroethylene	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
Dichloroethyl Ether	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Dichloromethane	A	A	A	A	A	A	A	C	C	C	C	C	C	C
1,2-Dichloropropane	A	A	A	A	A	A	A	C	C	C	C	C	C	C
1,3-Dichloropropene	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Dichlorvos	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Diesel Oil	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C
Diethanolamine	A	A	A	A	A	A	A	B	B	B	B	B	B	B
N,N-Diethylaniline	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Diethyl Carbonate	A	A	A	-	-	A	A	C	-	C	C	-	C	-
Diethyl Sulfate	A	A	A	A	A	A	A	C	C	C	C	C	-	C
3,3-Dimethoxybenzidine	A	A	A	A	A	A	A	C	C	C	C	C	-	-
Dimethylaminoazobenzene	A	A	A	A	A	A	A	-	-	-	-	-	-	-
N,N-Dimethyl Aniline	A	A	A	-	-	A	A	C	C	C	C	C	C	C
3,3-Dimethylbenzidine	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dimethyl Carbamoyl Chloride	A	A	A	C	C	A	A	C	C	C	C	C	C	C
Dimethyl Ether	A	A	A	A	A	A	A	B	C	B	B	C	B	B

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
Dimethylformamide	A	A	A	–	–	A	A	C	C	C	C	C	C	C
Dimethyl Hydrazine, Unsymmetrical	A	A	A	A	A	A	A	C	B	C	C	B	B	B
Dimethyl Phthalate	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Dimethyl Sulfate	A	A	A	A	A	A	A	C	C	C	C	C	–	C
4,6-Dinitro-o-Cresol and Salts	A	A	A	A	A	A	A	C	C	C	C	C	C	C
2,4-Dinitrophenol	A	A	A	–	–	A	A	C	C	C	C	C	C	C
2,4-Dinitrotoluene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dioxane	A	A	A	A	A	A	A	C	C	C	C	C	C	B
1,2-Diphenylhydrazine	A	A	A	A	A	A	A	C	B	C	C	B	–	–
Diphyl DT	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dowfrost	A	A	A	A	A	A	A	B	B	B	B	B	–	B
Dowfrost HD	A	A	A	A	A	A	A	B	B	B	B	B	–	B
Dowtherm 4000	A	A	A	A	A	A	A	B	B	B	B	B	B	B
Dowtherm A	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dowtherm E	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dowtherm G	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dowtherm HT	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dowtherm J	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dowtherm Q	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Dowtherm SR-1	A	A	A	A	A	A	A	B	B	B	B	B	B	B
Epichlorohydrin	A	A	A	A	A	A	A	C	C	C	C	C	C	B
1,2-Epoxybutane	A	A	A	A	A	A	A	–	C	–	–	C	C	C
Ethane	A	A	A	A	A	A	A	A	B	B	A ¹²	B	B	C
Ethers	A	A	A	A	A	A	A	B	C	B	B	C	B	B
Ethyl Acetate	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Ethyl Acrylate	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	B
Ethyl Alcohol ¹⁰	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethylbenzene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Ethyl Carbamate	A	A	A	A	A	A	A	C	C	C	C	C	B	B
Ethyl Cellulose	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethyl Chloride	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Ethyl Ether	A	A	A	A	A	A	A	B	C	B	B	C	B	B
Ethyl Hexoate	A	A	A	A	A	A	A	C	–	C	C	–	–	B
Ethylene	A	A	A	A	A	A	A	A	B	B	A	B	B	C
Ethylene Bromide	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Ethylene Dibromide	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Ethylene Dichloride	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Ethylene Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethyleneimine	–	–	A	–	–	A	A	C	C	C	C	C	C	C
Ethylene Oxide	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
Ethylene Thiourea	A	A	A	A	A	A	A	–	–	–	–	–	C	C
Ethylidene Chloride	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Ferric Chloride	A	A	A	C	C	A	A	A	A	A	B	B	B	B ⁴
Ferric Phosphate	A	A	A	–	–	A	A	B	B	B	B	B	B	B
Ferric Sulfate	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Fluorine, Gas	C	C	C	C	C	C	C	C	C	C	C	C	C	C

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
Fluorine, Liquid	C	C	C	C	C	C	C	C	C	C	C	C	C	C
Fluorine Dioxide	C	C	C	C	C	C	C	C	C	C	C	C	C	C
Formaldehyde	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A	B	A	A	B	B	A
Formic Acid	A	A	A	B	B	A	A	C	-	C	C	-	B	B
Fuel Oil	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C
Fuel Oil, Acid	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C
Furfural	A	A	A	A	A	A	A	C	C	C	C	C	B	B
Gasoline, Refined	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Sour	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Gelatin	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Glucose	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Glue, Protein Base	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Glycerine, Glycerol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Glycol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Grain Alcohol ¹⁰	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Grease, Petroleum Base	A	A	A	A	A	A	A	A	C	A	A	C	-	C
Green Sulfate Liquor	C	B	A	-	A	A	A	C	C	C	C	C	C	C
Heptachlor	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Heptane	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Hexachlorobenzene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Hexachlorobutadiene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Hexachlorocyclopentadiene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Hexachloroethane	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Hexadecane	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Hexamethylene Diisocyanate	A	A	A	A	A	A	A	-	C	-	-	C	-	C
Hexamethylphosphoramide	A	A	A	A	A	A	A	-	C	-	-	C	-	-
Hexane	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Hexone	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Hydraulic Oil, Mineral	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C
Synthetic	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Hydrazine	A	A	A	A	A	A	A	C	B	C	C	B	B	B
Hydrobromic Acid	A	A	A	C	C	A	A	C	C	C	C	C	C	C
Hydrochloric Acid	A	A	A	C	C	A	A	C	C	C	C	C	C	C
Hydrocyanic Acid	A	A	A	A	A	A	A	A	B	A	A	B	B	A
Hydrofluoric Acid, up to Anhydrous, 150°F & below	C	C	A	C	C	A	A	C	C	C	C	C	C	C
Less than 65%, Above 150°F	C	C	A	C	C	A	A	C	C	C	C	C	C	C
65% to Anhydrous, Above 150°F	C	C	-	C	C	A	A	C	C	C	C	C	C	C
Anhydrous	C	C	C	C	C	A	A	C	C	C	C	C	C	C
Hydrofluorosilicic Acid	C	C	A	C	C	A	A	C	C	C	C	C	C	C
Hydrofluosilicic Acid	C	C	A	C	C	A	A	C	C	C	C	C	C	C
Hydrogen	A	A	A	A	A	A	A	A	A	B	A	A	A	A
Hydrogen Bromide	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Hydrogen Fluoride	C	C	C	C	C	A	A	C	C	C	C	C	C	C
Hydrogen Peroxide, 10%	A	A	A	A	A	A	A	B	B	B	B	B	B	B
10-90%	A	A	A	B	B	A	C	B	-	B	B	-	C	B
Hydrogen Sulfide, Dry or Wet	A	A	A	A	A	A	A	B	B	B	B	B	B	B

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
Hydroquinone	A	A	A	A	A	A	A	C	B	C	C	B	C	C
Iodine Pentafluoride	-	-	-	-	-	-	C	C	C	C	C	C	C	C
Iodomethane	A	A	A	A	A	A	A	C	C	C	C	C	B	-
Isobutane	A	A	A	A	A	A	A	A	C	B	A ¹²	C	B	C
Isooctane	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Isophorone	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Isopropyl Alcohol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Jet Fuels (JP Types)	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Kerosene	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Lacquer Solvents	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Lacquers	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Lactic Acid, 150°F and below	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Above 150°F	A	A	A	A	A	A	A	-	-	-	-	-	-	-
Lime Saltpeter (Calcium Nitrates)	A	A	A	-	-	A	C	B	B	B	B	B	B	B
Lindane	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Linseed Oil	A	A	A	A	A	A	A	A	B	A	A	B	A	B
Lithium Bromide	A	A	A	A	A	A	A	A	-	A	A	-	A	A
Lithium, Elemental	C	C	C	C	C	C	C	C	C	C	C	C	C	C
Lubricating Oils, Mineral or Petroleum Types	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C
Refined	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C
Sour	A	A	A	A	A	A	A	B	B	B	B	B	B	C
Lye	C	B	A ⁶	C	A ⁶	A ¹¹	A ⁶	C	C	C	C	C	C	C
Magnesium Chloride	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Magnesium Hydroxide	A	A	A	A	A	A	A	B	B	B	B	B	B	B
Magnesium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Maleic Acid	A	A	A	A	A	A	A	B	B	B	B	B	B	A
Maleic Anhydride	A	A	A	A	A	A	A	C	-	C	C	-	C	C
Mercuric Chloride	A	A	A	C	C	A	A	A	A	A	A	A	B	A
Mercury	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Methane	A	A	A	A	A	A	A	A	B	B	A	C	B	C
Methanol, Methyl Alcohol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Methoxychlor	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Methylacrylic Acid	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Methyl Alcohol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
2-Methylaziridine	-	-	A	-	-	A	A	C	C	C	C	C	C	C
Methyl Bromide	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Methyl Chloride	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Methyl Chloroform	A	A	A	A	A	A	A	C	C	C	C	C	C	C
4,4 Methylene Bis(2-chloroaniline)	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Methylene Chloride	A	A	A	A	A	A	A	C	C	C	C	C	C	C
4,4-Methylene Dianiline	A	A	A	A	A	A	A	C	C	C	C	C	C	-
Methylene Diphenyldiisocyanate	A	A	A	-	-	A	A	C	C	C	C	C	C	-
Methyl Ethyl Ketone	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Methyl Hydrazine	A	A	A	A	A	A	A	C	B	C	C	B	B	B
Methyl Iodide	A	A	A	A	A	A	A	C	C	C	C	C	B	-
Methyl Isobutyl Ketone (MIBK)	A	A	A	A	A	A	A	C	C	C	C	C	C	B

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
Methyl Isocyanate	A	A	A	A	A	A	A	–	C	–	–	C	–	–
Methyl Methacrylate	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
N-Methyl-2-Pyrrolidone	A	A	A	A	A	A	A	C	B	C	C	B	–	–
Methyl Tert. Butyl Ether (MTBE)	A	A	A	A	A	A	A	B	C	B	B	B	C	C
Milk ¹⁰	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Mineral Oils	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C
Mobiltherm 600	A	A	A	A	A	A	A	A	C	A	A	C	–	C
Mobiltherm 603	A	A	A	A	A	A	A	A	C	A	A	C	–	C
Mobiltherm 605	A	A	A	A	A	A	A	A	C	A	A	C	–	C
Mobiltherm Light	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Molten Alkali Metals	C	C	C	C	C	C	C	C	C	C	C	C	C	C
Monomethylamine	A	A	A	A	A	A	A	C	B	C	C	B	A	B
MultiTherm 100	A	A	A	A	A	A	A	A	C	A	A	C	B	C
MultiTherm 503	A	A	A	A	A	A	A	A	C	A	A	C	–	C
MultiTherm IG-2	A	A	A	A	A	A	A	A	C	A	A	C	B	C
MultiTherm PG-1	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Muriatic Acid	A	A	A	C	C	A	A	C	C	C	C	C	C	C
Naphtha	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Naphthalene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Naphthols	A	A	A	–	–	A	A	–	–	–	–	–	–	–
Natural Gas	A	A	A	A	A	A	A	A	B	B	A ¹²	B	B	B
Nickel Chloride	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Nickel Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Nitric Acid, Less than 30%	A	A	A	A	A	A	C	C	C	C	C	C	C	C
Above 30%	A	A	A	A	A	A	C	C	C	C	C	C	C	C
Crude	A	A	A	–	–	A	C	C	C	C	C	C	C	C
Red Fuming	A	A	A	B	B	A	C	C	C	C	C	C	C	C
Nitrobenzene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
4-Nitrobiphenyl	A	A	A	A	A	A	A	C	C	C	C	C	C	C
2-Nitro-Butanol	A	A	A	–	–	A	–	C	–	C	C	–	C	–
Nitrocalcite (Calcium Nitrate)	A	A	A	–	–	A	C	B	B	B	B	B	B	B
Nitrogen	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Nitrogen Tetroxide	A	A	A	–	–	A	–	C	C	C	C	C	C	C
Nitrohydrochloric Acid (Aqua Regia)	A	A	A	B	B	A	C	C	C	C	C	C	C	C
Nitromethane	A	A	A	A	A	A	A	C	–	C	C	–	C	–
2-Nitro-2-Methyl Propanol	A	A	A	–	–	A	–	C	–	C	C	–	C	–
Nitromuriatic Acid (Aqua Regia)	A	A	A	B	B	A	C	C	C	C	C	C	C	C
4-Nitrophenol	A	A	A	–	–	A	A	C	C	C	C	C	C	C
2-Nitropropane	A	A	A	A	A	A	A	C	–	C	C	–	C	C
N-Nitrosodimethylamine	A	A	A	A	A	A	A	B	B	B	B	B	–	–
N-Nitroso-N-Methylurea	A	A	A	–	–	A	A	–	–	–	–	–	–	–
N-Nitrosomorpholine	A	A	A	A	A	A	A	C	–	C	C	–	C	–
Norge Niter (Calcium Nitrate)	A	A	A	–	–	A	C	B	B	B	B	B	B	B
Norwegian Saltpeter (Calcium Nitrate)	A	A	A	–	–	A	C	B	B	B	B	B	B	B
N-Octadecyl Alcohol	A	A	A	A	A	A	A	A	A	A	A	A	–	A
Octane	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number														
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700	
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530								
Oil, Petroleum	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C	
Oils, Animal and Vegetable ¹⁰	A	A	A	A	A	A	A	A	C	A	A	C	B	B	
Oleic Acid	A	A	A	A	A	A	A	B	–	B	B	–	C	C	
Oleum	A	–	C	C	C	A	–	C	C	C	C	C	C	C	
Orthodichlorobenzene	A	A	A	A	A	A	A	C	C	C	C	C	C	C	
Oxalic Acid	A	A	A	B	B	A	A	C	–	C	C	–	B	B	
Oxygen, Gas	See Note 7							C	C	C	C	C	C	C	C
Ozone	A	A	A	A	A	A	C	C	C	C	C	C	C	C	
Palmitic Acid	A	A	A	A	A	A	A	A	B	A	A	B	B	A	
Paraffin	A	A	A	A	A	A	A	A	B	A	A	B	B	C	
Paratherm HE	A	A	A	A	A	A	A	A	C	A	A	C	B	C	
Paratherm NF	A	A	A	A	A	A	A	A	C	A	A	C	–	C	
Parathion	A	A	A	A	A	A	A	C	C	C	C	C	C	C	
Paraxylene	A	A	A	A	A	A	A	C	C	C	C	C	C	C	
Pentachloronitrobenzene	A	A	A	–	–	A	A	C	C	C	C	C	C	C	
Pentachlorophenol	A	A	A	A	A	A	A	C	C	C	C	C	C	C	
Pentane	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C	
Perchloric Acid	A	A	A	C	C	A	C	C	C	C	C	C	C	C	
Perchloroethylene	A	A	A	A	A	A	A	C	C	C	C	C	C	C	
Petroleum Oils, Crude	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C	
Refined	A	A	A	A	A	A	A	A	B	A	A ¹²	B	B	C	
Phenol	A	A	A	A	A	A	A	C	C	C	C	C	C	B	
p-Phenylenediamine	A	A	A	A	A	A	A	C	C	C	C	C	–	–	
Phosgene	A	A	A	B	B	A	A	C	–	C	C	–	–	B	
Phosphate Esters	A	A	A	A	A	A	A	C	C	C	C	C	C	B	
Phosphine	A	A	A	A	A	A	A	–	–	–	–	–	–	–	
Phosphoric Acid, Crude	C	C	A	C	B	A	A	C	C	C	C	C	C	C	
Pure, Less than 45%	A	A	A	A	A	A	A	C	C	C	C	C	C	C	
Pure, Above 45%, 150°F and below	B	B	A	B	B	A	A	C	C	C	C	C	C	C	
Pure, Above 45%, Above 150°F	C	B	A	C	B	A	A	C	C	C	C	C	–	–	
Phosphorus, Elemental	A	A	A	A	A	A	A	C	C	C	C	C	C	C	
Phosphorus Pentachloride	A	A	A	B	B	A	A	C	C	C	C	C	C	C	
Phthalic Acid	A	A	A	A	A	A	A	C	–	C	C	–	B	–	
Phthalic Anhydride	A	A	A	A	A	A	A	C	–	C	C	–	C	B	
Picric Acid, Molten	–	–	–	–	–	–	–	–	–	–	–	–	–	–	
Water Solution	A	A	A	A	A	A	A	B	B	B	B	B	B	B	
Pinene	A	A	A	A	A	A	A	A	C	A	A	C	B	C	
Piperidine	A	A	A	A	A	A	A	C	C	C	C	C	C	C	
Polyacrylonitrile	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Polychlorinated Biphenyls	A	A	A	A	A	A	A	C	C	C	C	C	C	C	
Potash, Potassium Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Potassium Acetate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Potassium Bichromate	A	A	A	A	A	A	C	A	B	A	A	B	B	A	
Potassium Chromate, Red	A	A	A	A	A	A	C	A	B	A	A	B	B	A	
Potassium Cyanide	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Potassium Dichromate	A	A	A	A	A	A	C	A	B	A	A	B	B	A	

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
Potassium, Elemental	C	C	C	C	C	C	C	C	C	C	C	C	C	C
Potassium Hydroxide	C	B	A ⁶	C	A ⁶	A ¹¹	A ⁶	C	C	C	C	C	C	C
Potassium Nitrate	A	A	A	A	A	A	–	B	B	B	B	B	B	B
Potassium Permanganate	A	A	A	A	A	A	–	B	–	B	B	–	B	B
Potassium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Producer Gas	A	A	A	A	A	A	A	A	C	B	A ¹²	C	B	C
Propane	A	A	A	A	A	A	A	A	C	B	A ¹²	C	B	C
1,3-Propane Sultone	A	A	A	–	–	A	A	–	–	–	–	–	–	–
Beta-Propiolactone	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Propionaldehyde	A	A	A	A	A	A	A	C	C	C	C	C	–	–
Propoxur (Baygon)	A	A	A	A	A	A	A	C	C	C	C	C	–	–
Propyl Nitrate	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Propylene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Propylene Dichloride	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Propylene Oxide	A	A	A	A	A	A	A	C	C	C	C	C	C	B
1,2-Propylenimine	–	–	A	–	–	A	A	C	C	C	C	C	C	C
Prussic Acid, Hydrocyanic Acid	A	A	A	A	A	A	A	A	B	A	A	B	B	A
Pyridine	A	A	A	B	B	A	A	C	C	C	C	C	C	B
Quinoline	A	A	A	B	B	A	A	C	C	C	C	C	C	C
Quinone	A	A	A	A	A	A	–	–	–	–	–	–	–	–
Refrigerants	See Specific Ratings Below													
10	A	A	A	B	B	A	A	C	C	C	C	C	C	C
11	A	A	A	A	A	A	A	A	C	B	A	C	C	C
12	A	A	A	A	A	A	A	A	A	B	A	A	A	A
13	A	A	A	A	A	A	A	A	A	B	A	A	A	A
13B1	A	A	A	A	A	A	A	A	A	B	A	A	A	A
21	A	A	A	A	A	A	A	C	C	C	C	C	A	C
22	A	A	A	A	A	A	A	B	B	B	B	B	A	A
23	A	A	A	A	A	A	A	C	A	C	C	A	A	A
31	A	A	A	A	A	A	A	C	A	C	C	A	A	A
32	A	A	A	A	A	A	A	A	A	B	A	A	A	A
112	A	A	A	A	A	A	A	A	C	B	A	C	A	C
113	A	A	A	A	A	A	A	A	A	B	A	A	A	C
114	A	A	A	A	A	A	A	A	A	B	A	A	A	A
114B2	A	A	A	A	A	A	A	A	C	B	A	C	A	C
115	A	A	A	A	A	A	A	A	A	B	A	A	A	A
123	A	A	A	A	A	A	A	C ³	C	C ³	C ³	C	A ³	C
124	A	A	A	A	A	A	A	C	A	C	C	A	A	A
125	A	A	A	A	A	A	A	–	A	–	–	A	A	A
134a	A	A	A	A	A	A	A	B	A	B	B	A	A	A
141b	A	A	A	A	A	A	A	A	–	B	A	–	A	–
142b	A	A	A	A	A	A	A	A	A	B	A	A	A	A
143a	A	A	A	A	A	A	A	–	A	–	–	A	A	A
152a	A	A	A	A	A	A	A	A	A	B	A	A	A	A
218	A	A	A	A	A	A	A	A	A	B	A	A	A	A
290	A	A	A	A	A	A	A	A	C	B	A	C	A	C

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
500	A	A	A	A	A	A	A	A	-	B	A	-	A	-
502	A	A	A	A	A	A	A	A	A	B	A	A	A	-
503	A	A	A	A	A	A	A	C	A	C	C	A	A	A
C316	A	A	A	A	A	A	A	A	A	B	A	A	A	A
C318	A	A	A	A	A	A	A	A	A	B	A	A	A	A
HP62	A	A	A	A	A	A	A	A	-	B	A	-	A	-
HP80	A	A	A	A	A	A	A	-	-	-	-	-	A	-
HP81	A	A	A	A	A	A	A	-	-	-	-	-	A	-
Salt Water	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Saltpeter, Potassium Nitrate	A	A	A	A	A	A	-	B	B	B	B	B	B	B
2,4-D Salts and Esters	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Sewage	A	A	A	A	A	A	A	A	B	A	A	B	B	B
Silver Nitrate	A	A	A	A	A	A	-	B	A	B	B	A	A	A
Skydrols	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Soap Solutions	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Soda Ash, Sodium Carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Bicarbonate, Baking Soda	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Bisulfate, Dry	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Bisulfite	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Sodium Chlorate	A	A	A	A	A	A	A	C	-	C	C	-	C	C
Sodium Chloride	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Sodium Cyanide	C	C	A	C	C	A	A	C	C	C	C	C	C	C
Sodium, Elemental	C	C	C	C	C	C	C	C	C	C	C	C	C	C
Sodium Hydroxide	C	B	A ⁶	C	A ⁶	A ¹¹	A ⁶	C	C	C	C	C	C	C
Sodium Hypochlorite	A	A	A	B	B	A	-	C	-	C	C	-	C	C
Sodium Metaborate Peroxyhydrate	A	A	A	B	B	A	C	B	B	B	B	B	B	B
Sodium Metaphosphate	B	A	A	B	A	A	A	A	A	A	A	A	A	A
Sodium Nitrate	A	A	A	A	A	A	-	B	B	B	B	B	B	B
Sodium Perborate	A	A	A	B	B	A	C	B	B	B	B	B	B	B
Sodium Peroxide	A	A	A	A	A	A	C	C	C	C	C	C	C	C
Sodium Phosphate, Monobasic	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Dibasic	B	B	A	B	A	A	A	A	A	A	A	A	A	A
Tribasic	C	B	A	C	A	A	A	A	A	A	A	A	A	A
Sodium Silicate	B	B	A	B	A	A	A	B	B	B	B	B	B	B ⁴
Sodium Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Sulfide	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Superoxide	A	A	A	A	A	A	C	C	C	C	C	C	C	C
Sodium Thiosulfate, "Hypo"	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Soybean Oil ¹⁰	A	A	A	A	A	A	A	A	C	A	A	C	B	B
Stannic Chloride	A	A	A	C	C	A	A	B	B	B	B	B	-	B
Steam, Saturated, to 150 psig ¹³	A	A	A	A	A	A	A	A	A	A	A ⁹	A	A	A
Superheated	-	-	-	-	-	-	-	C	C	A	C	C	C	C
Stearic Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Stoddard Solvent	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Styrene	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
Styrene Oxide	A	A	A	A	A	A	A	C	C	C	C	C	C	C

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001 CP-3900	3200 3400 CP-3920	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
Sulfur Chloride	A	A	A	C	C	A	A	C	C	C	C	C	C	C
Sulfur Dioxide	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Sulfur, Molten	A	A	A	A	A	A	A	C	C	C	C	C	B	C
Sulfur Trioxide, Dry	A	A	A	A	A	A	-	C	C	C	C	C	C	C
Wet	A	A	A	B	B	A	B	C	C	C	C	C	C	C
Sulfuric Acid, 10%, 150°F and below	A	A	A	B	B	A	-	C	C	C	C	C	C	C
10%, Above 150°F	A	A	A	C	C	A	-	-	C	-	-	C	C	C
10-75%, 500°F and below	A	A	A	C	C	A	-	-	C	-	-	C	C	C
75-98%, 150°F and below	A	A	B	C	C	A	C	C	C	C	C	C	C	C
75-98%, 150°F to 500°F	A	B	B	C	C	A	C	C	C	C	C	C	C	C
Sulfuric Acid, Fuming	A	-	C	C	C	A	C	C	C	C	C	C	C	C
Sulfurous Acid	A	A	A	B	B	A	-	B	B	B	B	B	-	-
Syltherm 800	A	A	A	A	A	A	A	B	B	B	B	B	B	B
Syltherm XLT	A	A	A	A	A	A	A	B	B	B	B	B	B	B
Tannic Acid	A	A	A	- ^B	- ^B	A	A	A	A	A	A	A	A	A
Tar	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Tartaric Acid	A	A	A	A	A	A	A	A	A	A	A	A	A	A
2,3,7,8-TCDB-p-Dioxin	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Tertiary Butyl Amine	A	A	A	A	A	A	A	B	-	B	B	-	C	B
Tetrabromoethane	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Tetrachlorethane	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Tetrachloroethylene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Tetrahydrofuran, THF	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Therminol 44	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Therminol 55	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Therminol 59	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Therminol 60	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Therminol 66	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Therminol 75	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Therminol D12	A	A	A	A	A	A	A	B	C	B	B	C	B	C
Therminol LT	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Therminol VP-1	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Therminol XP	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Thionyl Chloride	A	A	A	C	C	A	A	C	C	C	C	C	C	C
Titanium Sulfate	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Titanium Tetrachloride	A	A	A	C	C	A	A	B	C	B	B	C	C	C
Toluene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
2,4-Toluenediamine	A	A	A	A	A	A	A	-	C	-	-	C	C	C
2,4-Toluenediisocyanate	A	A	A	-	-	A	A	C	C	C	C	C	C	B
Toluene Sulfonic Acid	A	A	A	-	-	A	A	C	C	C	C	C	C	C
o-Toluidine	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Toxaphine	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Transformer Oil (Mineral Type)	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Transmission Fluid A	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Trichloroacetic Acid	A	A	A	C	C	A	A	C	C	C	C	C	C	C
1,2,4- Trichlorobenzene	A	A	A	A	A	A	A	C	C	C	C	C	C	C

Call Gasket Applications Engineering at 1-800-448-6688 for specific recommendations.

WARNING:

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues.

Chemical Resistance of Garlock Compressed Sheet and GYLON®

Medium	Garlock Style Number													
	GYLON®							IFG 5500 G-9900 9850	9800	ST-706	3000 3001	3200 3400	3300 3800	IFG 5507 3700
	3500	3565 3504	3510	3560	3561	3535 3540 3545	3530							
1,1,2-Trichloroethane	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Trichloroethylene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
2,4,5-Trichlorophenol	A	A	A	-	-	A	A	C	C	C	C	C	C	C
2,4,6-Trichlorophenol	A	A	A	-	-	A	A	C	C	C	C	C	C	C
Tricresylphosphate	A	A	A	A	A	A	A	C	C	C	C	C	C	B
Triethanolamine	A	A	A	-	-	A	A	B	B	B	B	B	B	B
Triethyl Aluminum	A	A	A	-	-	A	A	C	-	C	C	-	C	-
Triethylamine	A	A	A	A	A	A	A	B	B	B	B	B	B	A
Trifluralin	A	A	A	A	A	A	A	C	C	C	C	C	C	C
2,2,4-Trimethylpentane	A	A	A	A	A	A	A	A	C	A	A ¹²	C	B	C
Tung Oil	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Turpentine	A	A	A	A	A	A	A	A	C	A	A ¹²	C	C	C
UCON Heat Transfer Fluid 500	A	A	A	A	A	A	A	A	B	A	A	B	B	B
UCON Process Fluid WS	A	A	A	A	A	A	A	A	B	A	A	B	B	B
Urea, 150°F and below	A	A	A	A	A	A	A	B	-	-	B	-	A	A
Above 150°F	A	A	A	A	A	A	A	-	-	-	-	-	-	-
Varnish	A	A	A	A	A	A	A	B	C	B	B	C	C	C
Vinegar ¹⁰	A	A	A	A	A	A	A	B	B	B	B	B	A	A
Vinyl Acetate	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	B	C	B	B	C	B	B
Vinyl Bromide	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
Vinyl Chloride	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
Vinylidene Chloride	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	A ¹	C	C	C	C	C	C	C
Vinyl Methacrylate	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Water, Acid Mine, with Oxidizing Salt	A	A	A	C	C	A	-	B	-	B	B	-	B	-
No Oxidizing Salts	A	A	A	A	A	A	A	A	-	A	A	-	B	A
Water, Distilled	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Return Condensate	A	A	A	A	A	A	A	A	A	A	A	-	-	A
Seawater	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Tap	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Whiskey and Wines ¹⁰	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Wood Alcohol	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Xceltherm 550	A	A	A	A	A	A	A	B	C	B	B	C	B	C
Xceltherm 600	A	A	A	A	A	A	A	A	C	A	A	C	B	C
Xceltherm MK1	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Xceltyherm XT	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Xylene	A	A	A	A	A	A	A	C	C	C	C	C	C	C
Zinc Chloride	A	A	A	B	B	A	A	A	A	A	A	A	A	A
Zinc Sulfate	A	A	A	A	A	A	A	A	A	A	A	A	A	A

Key: A = Suitable; B = Depends on operating conditions; C = Unsuitable; - = No data or insufficient evidence

NOTES:

- Consult the factory regarding your specific applications.
- IFG® Style 5507 is rated "B".
- There have been conflicting field reports concerning the suitability of NBR and neoprene bound gaskets in 123. End users should take note.
- IFG® Style 5507 is rated "A".
- Some chromium plating baths contain fluorides that can attack silica and silicate type fillers in some GYLON® styles. If the bath is known to contain little or no fluoride, all GYLON® styles should be suitable for use.
- These GYLON® styles can be expected to be suitable to 45-59% concentration at temperatures up to 250°F (121°C).
- Use GYLON® styles 3502, 3503, 3505, 3562, 3563. These styles are specially processed, cleaned and packaged for oxygen service.
- This GYLON® contains a stainless steel insert. There is a possibility that this might contribute traces of iron to form iron tannates, resulting in undesirable color in the tannic acid.
- Styles CP-3900, 3000 and 3001 are not preferred choices for steam service.
- If a gasketing material that conforms to FDA requirements is desired, contact factory for specific recommendations.
- These GYLON® styles can be expected to be suitable to 75% concentration at temperatures up to 400°F (204°C).
- Not a fire-tested material.
- For saturated steam above 150 psig, consult Garlock Engineering.

**Call Gasket Applications Engineering at 1-800-448-6688
for specific recommendations.**



Garlock Sealing Technologies
1666 Division Street
Palmyra, New York 14522 USA
1-315-597-4811
1-800-448-6688
Fax: 1-800-543-0598
1-315-597-3216

Visit the Garlock network:
www.garlock.net

Other Garlock facilities are located in:

Columbia, SC, USA	1-803-783-1880	Fax: 1-803-783-4279
Houston, TX, USA	1-281-459-7200	Fax: 1-281-458-0502
Sydney, Australia	61-2-9793-2511	Fax: 61-2-9793-2544
São Paulo, Brazil	55-11-884-9680	Fax: 55-11-884-9680
Brantford, Canada	1-519-753-8671	Fax: 1-519-758-2265
Sherbrooke, Canada	1-819-563-8080	Fax: 1-819-563-5620
Jebel Ali, Dubai	971-4-8833652	Fax: 971-4-8833682
West Yorkshire, England	44-1422-313600	Fax: 44-1422-313601
Saint-Étienne, France	33-4-7743-5100	Fax: 33-4-7743-5151
Neuss, Germany	49-2131-3490	Fax: 49-2131-349-222
Mexico City, Mexico	52555-567-7011	Fax: 52555-368-0418
Singapore	65-6-254-7372	Fax: 65-6-254-6708